



Date of issue : 05/01/2005
Last. mod. date : 10/05/2007

Product code**02025 RI-JET 145****Description**

Gloss white plasticised vinyl film, with good flexibility and conformability to curved surfaces.

Printing methods: solvent and UV inkjet.

Permanent adhesive with very good adhesion on glass and on a wide variety of substrates, except for apolar (PE, PP).

For promotional graphics and point of sale advertising with medium outdoor durability (ca. 3 years).

FACE MATERIAL

| | |
|-------------------|------------------------|
| Type | Plasticised vinyl film |
| Colour and Finish | White, Gloss |
| Weight | 110 g/m ² |
| Thickness | 80 µ |

ADHESIVE

| | |
|-------------------|-------------------|
| Reference | RI - AP |
| Type | Permanent acrylic |
| Min. Appl. Temp. | +10°C |
| Service Temp. | -30°C / +120°C |
| Shear | Excellent |
| Tack | Medium |
| Ultimate Adhesion | High |

RELEASE BACKING

| | |
|-------------------|----------------------|
| Type | 1 side clay coated |
| Colour and Finish | White |
| Weight | 135 g/m ² |
| Thickness | 135 µ |

CHEMICAL RESISTANCE

| | |
|----------------|--------------------|
| Detergent | No effect (24 Hrs) |
| Gasoline | No effect (1 Hrs) |
| SAE20 Motoroil | No effect (24 Hrs) |
| 10% HCl | No effect (10 min) |
| 10% NH4OH | No effect (10 min) |

Storage

The material must be stored at a temperature of 22°C +/- 2°C and 50% +/- 5% of Relative Humidity. Do not expose to direct sun light.

The area must be dry and clean. Please keep the material in the original packaging when not used in order to protect it from dust and contaminations.

All values presented in this data sheet are typical. Ritrama's data sheets provide only the general characteristics of the Product. It is the responsibility of the Customer and/or End User to determine that the Product is fit for the purpose for which the Customer and/or End User wish to use it. Ritrama can give no guarantee beyond the information given in the data sheet.

Ritrama S.p.A.
Ritrama S.p.A. Sassoferrato
Coating Ricofin S.r.l.
Ritrama S.A.
Ritrama Ltd.(UK)
Ritrama Inc. Minneapolis (USA)
Ritrama Inc. Cleveland (USA)

Tel. +39 02 955 459 1
Tel. +39 0732 97061
Tel. +39 02 955 430 1
Tel. +34 93 729 49 98
Tel. +44 161 786 1760
Tel. +1 612 378 2277
Tel. +1 216 851 2300

info@ritrama.it
info@ritrama.it
info@ricofin.it
ritrama@ritrama.es
sales@ritrama.co.uk
info@ritrama.com
info@ritrama.com



RITRAMA WINNER
OF THE BEST WIDE FORMAT SELF-ADHESIVE FILM