

# Ritrama Floor Talkers™

## Application Instructions

### Product Description

Ritrama Floor Talkers™ are designed to be applied to smooth, indoor floor surfaces in good condition, including waxed commercial PVC and ceramic tile.

### Floor/Surface Conditions

The floor must be clean and dry before applying graphics. Any wax, paints or coating on the floor surface must have good adhesion to the flooring substrate. Testing for product suitability by user is recommended prior to all applications.

### Application Instructions

Peel back about 1" of release liner from top of graphics. Fold and crease liner back. Position graphics starting with top of graphics. Apply firmly using plastic squeegee. Continue removing liner and smooth out graphics with squeegee. After entire graphic is applied, squeegee entire decal, working from centre out, to remove any air bubbles and to ensure good adhesion. Make sure edges are applied well.

Products should not be applied using wet method.

### Routine Maintenance

Wait 24 hours after application before cleaning or waxing floor. To maintain condition of graphics, avoid exposing graphics to heavy equipment traffic.

**CAUTION:** If edges of graphics begin lifting, replace graphics immediately to avoid risk of injury due to tripping hazard.

### Removal Instructions

Lift one edge of graphics and pull using short, quick strokes.

### Warranty Statement

Ritrama warrants that its Floor Graphics Products Floor Talkers™, constructed using only Ritrama-supplied components, including overlamine films and underlay, and installed in accordance with Ritrama written application instructions, will, for a period of six months after application, (a) adhere to Ritrama recommended floor surfaces and floor conditions, (b) be removable without damage to the surface and (c) maintain quality, ordinary wear and tear excepted.

## FLOOR TALKERS™

The static friction coefficient of FLOOR TALKERS has been determined in accordance with ASTM D 1894-73, DIN 53 375 and compared with the static friction coefficient of

gloss white soft vinyl - RI-145  
matt white soft vinyl - RI165.

Two tests were carried out:

the first one at 25 degrees C and 50 % RU for 24 hrs (please refer to the graphs labelled "DRY"), and the second one under wet conditions, using water to simulate the process of floor washing (referred to as "WET").

Ritrama UK Ltd  
Customer Information Services

26.04.1999

STATIC FRICTION COEFFICIENT  
Floor Talkers™

