



Ritrama S.p.A. Caponago Tel. +39 02 955 459 1
info@ritrama.it
 Ritrama S.p.A. Fabriano Tel. +39 0732 97061
info@ritrama.it
 Ritrama Ltd. (UK) Tel. +44 161 786 1760
sales@ritrama.co.uk
 Coating Ricofin S.r.l. Tel. +39 02 9210 6310
info@ricofin.it

Ritrama S.A. Tel +34 93 729 4998
info@ritrama.es
 Ritrama Inc. Minneapolis (USA) Tel. +1 612 378 2277
rdi@ritrama.com
 Ritrama Inc. Cleveland (USA) Tel. +1 216 851 2300
rdi@ritrama.com

Web site: www.ritrama.com

Automotive series

Date of issue: 24/06/2003

TECHNICAL SHEET

240μ GLOSS CLEAR POLYMERIC VINYL

Product code: 240μ GLOSS CLEAR

Description: Double layer gloss clear polymeric soft vinyl .
 Printing methods: screenprinting.
 Permanent adhesive with high adhesion and shear at high temperature too. Suitable for outdoor applications. Not Suitable for apolar substrates.(PE,PP).
 For stone guard application in the automotive industry.
 For special applications.

TECHNICAL DATA

<u>FACE MATERIAL</u>		<u>ADHESIVE</u>	
Type	Double layer soft polymeric PVC	Reference	RI ASP8A
Colour and finish	Clear, gloss without PE protection	Type	Permanent acrylic (solvent based)
Thickness (ASTM D374-88)	240 ± 20μ	Weight (FTM-12)	40± 3g/m ²
Shrinkage (Rit. 042)	< 2 %	Min.appl.Temp.	+ 10 °C
		Service temp.	From -30 °C to +140 °C
		Peel 10' s.s. (FTM-1)	> 14 N/inch
		Peel 24h s.s. (FTM-1)	>16 N/inch
		Quick Stick (FTM-9)	>13 N/inch
		Shear s.s. (FTM-8)	>200 h
<u>RELEASE BACKING</u>		<u>CHEMICAL RESISTANCE</u>	
Type	Paper Bipe 1 side siliconised	Detergent	No effect (24H)
Colour	White	Gasoline	No effect (1 H)
Weight (ISO 536)	144 g/sqm ± 6%	SAE20 Motoroil	No effect (24 H)
		10% HCl	No effect (10min)
		10% NH4OH	No effect (10min)

All values presented in this data sheet are typical. The information is given in good faith but without warranty.