



Scapa A1179 Acrylic Foam Tape

DESCRIPTION

Scapa A1179 is a 1.14mm thick standard performance acrylic foam bonding tape. The product is available in white and grey. Scapa A1179 consists of an acrylic foam adhesive with an acrylic core and a Scapa branded paper release liner.

APPLICATIONS

- Signage manufacturing.
- Trim attachment.
- Metal stiffener bonding.
- Georgian bars.

PRODUCT BENEFITS

- Service Temperature -30°C to $+80^{\circ}\text{C}$ {continuous}
- Temperature Short Term Performance Range -30°C to $+130^{\circ}\text{C}$ {maximum duration of 1 hour}
- High adhesion to a wide variety of substrates
- Good resistance to solvents and moisture
- Excellent ageing and weathering properties
- Very good Ultra violet {UV} light resistant
- Resistance to abrasion, corrosion and moisture
- Suitable for indoor and outdoor environments
- No known hazards associated with this product
- Good anti-vibration properties
- Pre-determined dimensional bonding tape reduces waste
- Clean to use

TECHNICAL PROPERTIES

	Unit	Nominal Value	Test Method
180° Peel Adhesion	N/25mm	40	Scapa F9
Dynamic Shear	Ncm ⁻²	53	Scapa F11
Static Shear {1Kg/6.25cm ² }	Hours	500+	Scapa F7
Rolling Ball Tack Test	mm	310	Scapa F 23

STANDARD PRESENTATION

- Formats Logs, Rolls
- Thickness: 1.1 mm (± 0.1)
- Core: 76mm

RECOMMENDATIONS

Surfaces must be clean, dry, free from grease and dirt.

Recommended cleaning agent is Propan-2-ol, {IPA}. Please note manufacturer's safety instructions should be followed and customers are recommended to ensure compatibility of the solvent with their substrate.

Ideal bonding substrates are those which are: clean, dry, flat, smooth, dust free & non-porous

Application temperature: +10 °C to + 40 °C. Shelf life of 1 year

Low temperatures may increase the risk of condensation, reducing the tack of the product.

Life expectancy will vary with temperature and humidity.

Product may be applied by hand direct from a roll applying even pressure.

Customers are recommended to make their own assessment of our products under their own conditions, for their own requirements.