



Ritrama S.p.A. Caponago Tel. +39 02 955 459 1  
[info@ritrama.it](mailto:info@ritrama.it)  
Ritrama S.p.A. Fabriano Tel. +39 0732 97061  
[info@ritrama.it](mailto:info@ritrama.it)  
Ritrama Ltd.(UK) Tel. +44 161 786 1760  
[sales@ritrama.co.uk](mailto:sales@ritrama.co.uk)  
Coating Ricofin S.r.l. Tel. +39 02 9210 6310  
[info@ricofin.it](mailto:info@ricofin.it)

Ritrama S.A. Tel +34 93 729 4998  
[info@ritrama.es](mailto:info@ritrama.es)  
Ritrama Inc. Minneapolis (USA) Tel. +1 612 378 2277  
[rdi@ritrama.com](mailto:rdi@ritrama.com)  
Ritrama Inc. Cleveland (USA) Tel. +1 216 851 2300  
[rdi@ritrama.com](mailto:rdi@ritrama.com)  
Web site: [www.ritrama.com](http://www.ritrama.com)

Date of issue: 30-03-2006

## TECHNICAL SHEET

# RI JET 30 FLEXILAM CAST CLEAR

**Product code:** RI JET 30 FLEXILAM CAST CLEAR

**Description:** Gloss clear CAST soft vinyl.  
Ultra thin overlamination film ideal for vehicle wraps.  
Recommended for overlaminating of RI JET 50 CAST white,  
RI JET 70 blackout, RI JET 75 white and RI JET 75 blackout.

**Size available:** h 1370 - 1520 mm x 50 m

### TECHNICAL DATA

<u>FACE MATERIAL</u>		<u>ADHESIVE</u>	
Type	Cast vinyl	Reference	RI - ASP 26
Colour and finish	Gloss, clear	Type	Acrylic permanent (solvent based)
Caliper	30 $\mu$ $\pm$ 10%	Min. appl. temp.	+ 10°C
Substance	50 g/sqm $\pm$ 10%	Service temp.	-20°C to +120°C
Durability ( Outdoor application)	7 years	Cohesion	Very good
<u>RELEASE BACKING</u>		Tack	High
Type	2 side PE coated Kraft paper	Ultimate adhesion	Good
Colour	white	<u>CHEMICAL RESISTANCE</u>	
Substance	144 g/sqm $\pm$ 10%	Detergent	No effect (24 Hrs)
Caliper	150 $\mu$ $\pm$ 10%	Gasoline	No effect (1 H)
		SAE20 Motoroil	No effect (24 Hrs)
		10% HCl	No effect (10 min)
		10% NH4OH	No effect (10 min)

All values presented in this data sheet are typical. The information is given in good faith but without warranty.