



Ritrama S.p.A. Caponago Tel. +39 039 839215
info@ritrama.it
Ritrama S.p.A. Fabriano Tel. +39 0732 97061
info@ritrama.it
Ritrama Ltd. (UK) Tel. +44 161 786 1760
sales@ritrama.co.uk
Coating Ricofin S.r.l. Tel. +39 02 9210 6310
info@ricofin.it

Ritrama S.A. Tel +34 93 729 4998
info@ritrama.es
Ritrama Inc. Minneapolis (USA) Tel. +1 612 378 2277
rdi@ritrama.com
Ritrama Inc. Cleveland (USA) Tel. +1 216 851 2300
rdi@ritrama.com

Web site: www.ritrama.com

Date of issue: 30-10-2004

TECHNICAL SHEET

RI 2967 OVERLAMINATING Film Semi-matt

Product code: RI 2967

Description: Semi matt clear anti-reflection product suitable for long term indoor/outdoor lamination. Special additives give a high protection against UV rays. The PVC film allows the lamination of prints and posters made with LFDP both on flat and curved surfaces.

Size available: h1050 - 1310 - 1400-1530 mm x 50 – 100 m

TECHNICAL DATA

<u>FACE MATERIAL</u>		<u>ADHESIVE</u>	
Type	Plasticised vinyl film	Reference	RI-ASP 17
Colour and finish	Semi matt, clear	Type	Permanent acrylic (solvent based)
Caliper	70 μ \pm 10%	Min. appl. temp.	+10 $^{\circ}$ C
Substance	80 g/sqm \pm 10%	Service temp.	-30 $^{\circ}$ C to +120 $^{\circ}$ C
Shrinkage	1%	Cohesion	> 50h
		Quick Stick	> 13 N/Inch
		Ultimate adhesion	> 12 N/Inch
<u>RELEASE BACKING</u>		<u>CHEMICAL RESISTANCE</u>	
Type	1 side siliconised, glassine	Detergent	No effect (24 Hrs)
Colour	White	Gasoline	No effect (1 Hr)
Substance	63 g/sqm \pm 10%	SAE20 Motoroil	No effect (24 Hrs)
Caliper	55 μ \pm 10%	10% HCl	No effect (10 min)
		10% NH4OH	No effect (10 min)

All values presented in this data sheet are typical. The information is given in good faith but without warranty.