

## Ri-Mark Hybrid Etched Glass

**PRODUCT DESCRIPTION / BENEFITS** Ri-Mark Hybrid Etched Glass is the ideal choice for windows decoration with etched effect, ensuring privacy and allowing natural light transmission.

Ri-Mark Hybrid Etched Glass is a calendered vinyl with a mix of polymeric & monomeric plasticizers, UV stabilised, manufactured in such a way to ensure a uniform matt appearance, with a colour stability up to 5 years for outdoor use and up to 7 years for indoor use.

The very cohesive solvent-based adhesive provides an excellent dimensional stability and water resistance. The kraft liner is designed for trouble-free plotter cutting on a wide variety of computerised sign cutting equipment.

All products are REACH & RoHS compliant.

### TYPICAL USE

- Windows decoration on restaurants, bars, museums, showrooms, ...
- Privacy applications in banks, offices, homes, ...

### CONSTRUCTION

- **Face film:** 80 µm calendered vinyl with a mix of polymeric & monomeric plasticizers
- **Adhesive:** Permanent clear solvent-based acrylic
- **Release liner:** clay coated kraft paper 120 g/m<sup>2</sup> or

#### Products:

Cast with frosted finish: Code: 12795 - **Ri-Mark Hybrid Etched Glass Perm SB**

### CONVERTING METHOD

Specially developed for trouble-free plotter cutting on a wide variety of computerised sign cutting equipment. Can also be printed with solvent, eco-solvent, latex, and UV inkjet printing presses.

### APPLICATION METHOD / INSTRUCTIONS FOR USE

Wet application method is recommended at a temperature above 10°C on clean and degreased substrates such as glass and acrylic panels.

### EXPECTED DURABILITY

The expected vertical outdoor durability in Central Europe (zone 1) is:

- 5 years

This information is based on real file experience and artificial aging according to ISO 4892-2.

Note: Exposure to severe temperature and ultra-violet light will cause a quicker deterioration.

This applies also to polluted area, high altitude, horizontal applications, and south-facing exposure in north hemisphere.

### SHELF LIFE

Shelf life is 2 years, when stored at 23 °C and 50 % relative humidity conditions.

Higher temperatures and/or humidity levels will reduce product shelf life.

## Ri-Mark Hybrid Etched Glass

### PHYSICO-CHEMICAL PROPERTIES / TYPICAL VALUES

Face thickness, without adhesive	80 µm	ISO 534-80
Face thickness, with adhesive	100 µm	ISO 534-80
Tensile strength (machine direction)	> 20 N/cm	ISO 527
Elongation at break (machine direction)	>120%	ISO 527
Fire resistance on aluminium	Self-extinguishing	ISO 3795:1989
Dimensional stability (1 week @70 °C on glass)	0.4 mm	FTM 14
Adhesion on glass (20 minutes)	9 N/25mm	FTM 1
(24 hours)	15 N/25mm	
(1 week)	17 N/25mm	
Minimum application temperature	+10 °C	
Service temperature	From -40 °C to +90 °C	
One side siliconized clay coated paper liner	120 g/m <sup>2</sup>	ISO 536

### QUALITY CERTIFICATION



### DISCLAIMER

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.